

# PATENT ABSTRACTS OF JAPAN

(11)Publication number : 62-250073  
 (43)Date of publication of application : 30.10.1987

(51)Int.Cl.

C09C 1/56

(21)Application number : 61-093661

(71)Applicant : ASAHI CARBON KK

(22)Date of filing : 23.04.1986

(72)Inventor : INOUE YASUMOTO  
 ASAZUMA TAKAHARU


(54) CARBON BLACK HAVING MODIFIED SURFACE AND PRODUCTION THEREOF

(57)Abstract:

PURPOSE: To obtain the titled carbon black useful for rubber reinforcing and as a filler, having improved dispersibility and processing properties, by blending carbon black having large surface area with a solution of a p-phenylenediamine compound, etc., and drying at a specific temperature.



CONSTITUTION: (A) 100pts.wt. carbon black having  $\geq 130\text{m}^2/\text{g}$  specific surface area by nitrogen adsorption is blended with (B) an organic solvent (e.g. toluene, etc.) or water dispersion containing 0.5W50pts.wt. one or more compounds [e.g. N-(1-methylheptyl)-N'-phenyl-p-phenylenediamine, etc.] shown by formula I (R is isopropyl, 1,3-dimethylbutyl, 1-methylheptyl, phenyl, group shown by formula II or p-toluenesulfonyl), the solvent or water is removed and dried at  $150\text{W}200^\circ\text{C}$  to give the aimed compound wherein the component B is added to the surface of the component A.



## LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than  
the examiner's decision of rejection or  
application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's  
decision of rejection]

[Date of requesting appeal against examiner's  
decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office